

Sikaflex®-522 WEATHER RESISTANT, LOW EMISSION, ANTI-FUNGAL ADHESIVE SEALANT



Sikaflex®-522 is a low emission one-component adhesive sealant based on the Sika Silane Terminated Polymer (STP) technology that cures on exposure to atmospheric humidity. Sikaflex®-522 meets highest EHS standards with very low emissions as its formulation is isocyanate, solvent, PVC and phthalate free. Sikaflex®-522 contains fungicide, allowing it to meet the hygiene requirements for ventilation and air-conditioning systems and units according VDI 6022. It may also be used for sealing in food processing environments as well as on refrigerated trucks and stationary cold-storage containers according EN 1186, EN 13130 and CEN/TS 14234 standards.

Sikaflex®-522 is low odor, ageing and weathering resistant, bonds well to a wide variety of substrates without the need for special pre-treatments. It is suitable for interior and exterior elastic sealing and bonding applications on substrates such as timber, glass, metals, metal primers and paint coatings (2-part systems), ceramic materials and plastics.

## **TYPICAL APPLICATION AREAS**

- General machinery, body and frame sealing and bonding
- Hygiene, ventilation and air conditioning systems
- Store refrigerators and refrigerating rooms and trucks
- Food processing and packaging machinery
- Sealing and bonding in recreational vehicles

## **KEY PRODUCT FEATURES**

 Equipped with fungicide for ultimate mold and fungus resistance



Excellent ageing and weathering resistance



■ Meets highest EHS standards as it is free of isocyanate, solvents, PVC and phthalates




 Wide adhesion range, bonds well without the need for special pretreatments




TECHNICAL DATA	
Chemical base	1-Component STP
Colour	White
Non-sag properties	Good
Application temperature	5°C - 40°C
Skin time	30 minutes
Shore A-hardness	35
Tensile strength	1.5 N/mm <sup>2</sup>
Tear propagation resistance	6 N/mm <sup>2</sup>
Elongation at break	350%

-40°C to +90°C

4h 140°C / 1h 150°C



Durable and qualified joint seals in food cooling and transport can be achieved with Sikaflex®-522.



Service Temperature

Short term

Sealing and bonding of metal sheets in air treatment and ventilation systems with Sikaflex®-522 for ultimate mold and fungus-resistance.

## **SIKA SERVICES AG**

Tueffenwies 16 CH-8048 Zurich Phone: +41 (0) 58 436 40 40 Fax: +41 (0) 58 436 55 30

www.sika.com/industry

Our most current General Sales Conditions shall apply.
Please consult the Data Sheet prior to any use and processing.







