

PRODUCT DATA SHEET

Sika Boom[®]-120 Low Expansion

1-PART, LOW EXPANSION, POLYURETHANE FOAM FOR FITTING, FILLING AND INSULATING

DESCRIPTION

Sika Boom[®]-120 Low Expansion is a single-component, moisture-curing and self-expanding aerosol polyurethane foam.

USES

- For fitting, fixing, insulating and bonding wooden staircases, window sills, e.t.c.
- For filling connection joints around window and door frames, around air-conditioning vents and roller blind housings, e.t.c.
- For insulation against sound and cold, etc.
- Filling and sealing gaps, joints and cavities
- Filling of penetrations in walls
- Insulating electrical outlets and water pipes

CHARACTERISTICS / ADVANTAGES

- Easy and precise dosing – small consumption
- Particularly suitable for narrow joints
- Excellent mounting capacity and stability
- Excellent adhesion & filling capacity and high thermal & acoustical insulation value
- Retains elasticity
- Fast curing
- Mould-proof, water-proof, over paintable
- Good resistance to vibrations
- Returns to its original form after compression
- Very low post expansion
- Adheres to all construction materials, such as wood, concrete, metal, aluminium, aerated concrete, brick
- Cured foam dries rigid and can be trimmed, shaped and sanded.
- Excellent temperature insulation
- Effective sound dampening
- CFC / HFC-free
- Does not adhere to PTFE, PE and silicone

APPROVALS / CERTIFICATES

- Reaction to fire: Class B3 (DIN 4102)

PRODUCT INFORMATION

Composition	1-part Polyurethane, moisture curing	
Packaging	750 ml can, 850 g (12 cans per box)	
Colour	Light yellow	
Shelf life	12 months from date of production	
Storage conditions	Store in undamaged, original, sealed containers, in dry conditions and protected from direct sunlight at temperatures between +5°C and +25°C. Storage above +25 °C and below +5 °C shortens shelf life. The can has to be stored in a vertical position!	
Density	22 ± 3 kg/m ³	(ASTM D1622)
Compressive Strength	0.03 N/mm ² (at 23°C / 50% r.h.)	(DIN 53 421)

Reaction to Fire	B3	(DIN 4102-1)
Water Absorption	max. 1% by volume	(DIN 53428)
Thermal Conductivity	0,036 W/m.k (at 20°C)	(DIN 52612)
Service Temperature	-40 °C min./ +80 °C max.	

APPLICATION INFORMATION

Consumption	Consumption can be regulated by the strength of dispensing the foam.		
Yield	Volume (packaging)	Yield (L)	(ASTM C1536)
	750 ml can	30-45	
Ambient Air Temperature	+5°C min. / +30°C max.		
Substrate Temperature	+5°C min. / +30°C max.		
Curing Time	Full cured after 24 hours (at 23°C / 50% r.h.)		
Cutting Time	Width (cm)	Cutting time (min)	(ASTM C1620)
	1	20-45	
Tack free time	7±2 minutes	(ASTM C 1620)	

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Substrate must be clean, homogeneous, free from oils and grease, dust and loose or friable particles. Pre-dampen the substrate with clean water, this ensures that the foam cures optimally and prevents secondary foam expansion.

APPLICATION METHOD / TOOLS

Shake the can thoroughly before use (~ 20 times). Remove the small black lid from the Sika Boom®-120 Low Expansion can. Gently press the trigger of the dispenser tube to apply the foam. The foam should be at room temperature, if the foam is colder, place the batch in warm water (max. T = 40 °C) for about 20 min. Where small gaps have to be filled use the extension tube supplied with the product (the foam flow rate is lower with the extension tube). Take care to allow each layer to cure sufficiently. All fixings and components must be temporarily supported until the foam has hardened.

Try to use the entire quantity of foam within one application or within the same day.

CLEANING OF EQUIPMENT

Removal of fresh remnants from tools and application equipment can be carried out using Sika Boom® Cleaner / Sika® Remover-208. Hardened / cured material can only be mechanically removed.

IMPORTANT CONSIDERATIONS

- The aerosol-can temperature has to be +5°C min. and +30°C max. For best workability the aerosol-can temperature must be +20°C.
- The can should be kept in room temperature for at least 12 hours before the application.

- The cans should be stored and transported in vertical position.
- Protect the can from sun and temperatures above +50°C (explosion danger)
- For the proper curing of the foam sufficient moisture is necessary
- Do not use on PE, PP, Teflon, Silicone, Oil, Grease and other separating agents
- Cured foam is not resistant to UV light exposure
- Paint or coat the cured foam for best results in outdoor applications.
- Lower temperatures decrease yield and prolong curing time.
- Read safety and technical recommendations printed on the aerosol-can

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Hellas ABEE

15 Protomagias Str.
14568 Kryoneri
Attica-Greece
Tel.: +30 210 8160 600
Fax: +30 210 8160 606
www.sika.gr | sika@gr.sika.com



Product Data Sheet
Sika Boom®-120 Low Expansion
January 2019, Version 01.01
020514060000000093

SikaBoom-120LowExpansion-en-GR-(01-2019)-1-1.pdf