

**BUILDING TRUST** 

# PRODUCT DATA SHEET Sikadur-Combiflex<sup>®</sup> SG-10 P

## HIGH PERFORMANCE JOINT AND CRACK SEALING TAPE

## DESCRIPTION

Sikadur-Combiflex<sup>®</sup> SG-10 P is a flexible waterproofing tape based on modified flexible Polyolefin (FPO) with advanced adhesion properties. Thickness 1,0 mm. The product is part of the Sikadur Combiflex<sup>®</sup> SG System.

## USES

Sealing all types of joints and cracks in many different structures and applications including:

- Tunnels and culverts
- Hydroelectric power plants
- Sewage treatment plants
- Basements
- Water retaining structures
- Drinking water reservoirs
- Sealing of:
- Movement joints
- Construction joints
- Pipe penetrations
- Cracks
- Building components where differential settlement is expected

## **CHARACTERISTICS / ADVANTAGES**

- Advanced adhesion, no activation on site required
- Highly flexible high crack and joint bridging ability
- Good chemical resistance
- Weathering and UV-resistant
- Root penetration resistant
- Performs well within a wide range of temperatures
- Plasticiser-free
- Hot air weldable
- Can be used in contact with potable/drinking water

## **APPROVALS / CERTIFICATES**

- Drinking water AS/NZS 4020, Sikadur Combiflex<sup>®</sup> SG , ams Laboratories, Test report No. 1116525
- Drinking water KTW, Sikadur Combiflex<sup>®</sup> SG , HY, Certificate No. K-248079-14-Ko
- Root Resistance CEN/TS 14416, Sikadur Combiflex<sup>®</sup> SG, SKZ, Test report No. 89643/09
- Sanitary Compliance XP P 41-250, Sikadur Combiflex<sup>®</sup> SG , CARSO, Certificate No. 16 MAT LY 108
- Water Regulations up to 50 °C BS6920-1:2000, Sikadur Combiflex<sup>®</sup> SG, WRAS, Approval No. 1708503

## **PRODUCT INFORMATION**

Composition	Modified flexible Polyolefin (FPO)	
Packaging	1 roll of 25 m length	
Appearance / Colour	Flexible light grey membrane	
Thickness	1,0 mm	
Width	10, 15, 20, 25, 30, 40, 50, 100, 200 cm	
Length	25 m roll	
Shelf life	36 months from date of production	

Product Data Sheet Sikadur-Combiflex® SG-10 P August 2019, Version 01.01 020703150200000005 The product must be stored in original, unopened and undamaged sealed packaging in dry conditions. Opened and unprotected rolls must be used within 2 months. Always refer to packaging.

-	
35	(DIN 53505)
Pass	(CEN/TS 14416)
>12 N/mm <sup>2</sup>	(EN 12311-2)
> 650 %	(EN 12311-2)
Maximum permissible permanent elongation	<10 % of non-adhered tape width
Note: For higher joint movement, loop tape into the gap of the joint.	
> 50 N/mm	(EN12310-2)
> 300N/50 mm	(EN 12316-2)
> 400N/50 mm	(EN 12317-2)
Passed	(EN 495-5)
No cracks at -40 °C	
Euroclass E (EN ISO 11925-2, classification to EN 13501-1)	
Tested according to EN 1847. Contact Sika Technical Services for additional information.	
Artificial weathering: 7500 h passed	(EN ISO 4892-2/-3)
6 bar / 72h	(EN 1928-B)
Behaviour under hydrostatic pressure	
-40 °C min. to +60 °C max	
Refer to Sikadur Combiflex <sup>®</sup> SG System data sheet.	
ON	
+0 °C min. / +60 °C max. (dry conditions)	
	Pass         >12 N/mm²         > 650 %         Maximum permissible permanent elongation         Note: For higher joint movement, I         > 50 N/mm         > 300N/50 mm         > 400N/50 mm         Passed         No cracks at -40 °C         Euroclass E         Tested according to EN 1847. Continformation.         Artificial weathering:         7500 h passed         6 bar / 72h         Behaviour under hydrostatic press         -40 °C min. to +60 °C max         Refer to Sikadur Combiflex® SG Sys

### **TECHNICAL INFORMATION**

 
 Ambient Air remperature
 +0 °C min. / +60 °C max. (dry conditions)

 Substrate Temperature
 +5 °C min. / +45 °C max. (Sikadur® epoxy adhesive temperature limits apply)

## **APPLICATION INSTRUCTIONS**

#### **APPLICATION METHOD / TOOLS**

Reference must be made to further documentation where applicable, such as relevant method statement, application manual and installation or working instructions.

## FURTHER INFORMATION

- Sikadur Combiflex<sup>®</sup> SG System Data Sheet
- Sika Method Statement: Sikadur Combiflex<sup>®</sup> SG System

## **IMPORTANT CONSIDERATIONS**

 Refer to the Sikadur Combiflex<sup>®</sup> SG System Sika Method Statement and System Data Sheet.

## **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product

**BUILDING TRUST** 

Product Data Sheet Sikadur-Combiflex® SG-10 P August 2019, Version 01.01 020703150200000005



Data Sheet for the exact description of the application fields.

## **ECOLOGY, HEALTH AND SAFETY**

#### REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheed following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1% (w/w).

## **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika Hellas ABEE

15 Protomagias Str. 14568 Kryoneri Attica-Greece Tel.: +30 210 8160 600 Fax: +30 210 8160 606 www.sika.gr | sika@gr.sika.com





Product Data Sheet Sikadur-Combiflex® SG-10 P August 2019, Version 01.01 02070315020000005

Sikadur-CombiflexSG-10P-en-GR-(08-2019)-1-1.pdf



**BUILDING TRUST**