

PRODUCT DATA SHEET

Sigunit® L-5601 AF

SHOTCRETE ACCELERATOR



DESCRIPTION

Sigunit® L-5601 AF is a high-performance liquid, alkali-free, set accelerator for shotcrete.

USES

Sigunit® L-5601 AF is suitable for both dry and wet spraying processes and it is used for:

- Excavation stabilisation in tunnelling and mining
- Rock, slope and trench stabilisation
- High quality lining shotcrete

CHARACTERISTICS / ADVANTAGES

Sigunit® L-5601 AF has the following characteristics and advantages:

- High early strength development
- Alkali-free
- Minimal strength loss of the accelerated concrete
- No pollution of groundwater by leached out alkalis
- Distinct reduction of rebound and dust
- Improved bond of shotcrete to the substrate
- Chloride-free, no negative affect on reinforcement steel

APPROVALS / STANDARDS

Non-alkaline sprayed concrete set accelerating admixtures according to EN 934-5 (T.2). DoP 021401011000000156 1095, and provided with the CE Mark.

PRODUCT INFORMATION

Chemical base	Inorganic aluminium complexes
Packaging	Bulk supply IBC
Appearance / Colour	Whitely suspension
Shelf life	Three months from date of production if stored in original, undamaged and sealed containers.
Storage conditions	Storage at temperatures between 5°C and 30°C. Protect from direct sunlight, frost and contamination. Use clean containers when delivered in bulk. In case of separation of Sigunit® L-5601 AF the suspension has to be homogenised before using. Sigunit® L-5601 AF must not be stored in standard steel containers.
Density	~ 1.44 kg/L
pH-Value	~ 2.5
Conventional Dry Material Content	~ 55 %
Viscosity	≤ 400 mPa s at 20°C

Total Chloride Ion Content ≤ 0.1 %

Equivalent Sodium Oxide ≤ 1.0 %

TECHNICAL INFORMATION

Specific Advice	Sigunit® L-5601 AF is added at the nozzle. Accurate and constant dosing into the concrete flow is essential.
Concrete Mix Design	The suitability of the proposed mix design must be tested in field trials before commencement of the project. High quality shotcrete requires a w/c ratio of less than 0.5 and a flow table spread of more than 500 mm. Temperature of basic mix must be higher than 15°C.
Substrate	The substrate must be clean, free of loose stones and free of water under hydrostatic pressure.

APPLICATION INFORMATION

Recommended Dosage	The correct dosage must be determined by preliminary testing. For layer thicknesses of up to 10 cm applied in one pass, the recommended accelerator dosage is between 6 % and 9 % by weight of binder. Lower ambient and basic mix temperatures require higher dosage of accelerator.
---------------------------	---

LIMITATIONS

The accelerator's effect depends on the content, age and type of cement, as well as on the shotcrete temperature. Furthermore, the shotcrete quality is widely affected by the substrate, the applied layer thickness, the spraying process, the quality of equipment and the application technique. The w/c ratio of the basic concrete mix in the wet spraying process, and the quantity of gauging water in the dry spraying process are also parameters influencing the acceleration effect of Sigunit® L-5601 AF.

When using sulphate resistant cements strength development can be slower.

Sigunit® L-5601 AF is not compatible with alkaline shotcrete accelerators. Before using Sigunit® L-5601 AF the accelerator hoses must be cleaned thoroughly. The use of Sigunit® L-5601 AF requires technically correct dosing and conveying / spraying technology. Metal parts of the pump and piping that come into direct contact with Sigunit® L-5601 AF must be made of stainless steel.

Contact your local Sika company for any additional technical support required.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control. All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Hellas ABEE
15 Protomagias Str.
14568 Kryoneri
Attica-Greece
Tel.: +30 210 8160 600
Fax: +30 210 8160 606
www.sika.gr | sika@gr.sika.com



SigunitL-5601AF_en_GR_(02-2017)_1_1.pdf

Product Data Sheet
Sigunit® L-5601 AF
February 2017, Version 01.01
021401011000000156