

## PRODUCT DATA SHEET

# SikaShield® P47 S 4 mm

Plastomeric bituminous membrane surfaced with sand and flexible at -10 °C

### DESCRIPTION

SikaShield® P47 S 4 mm is an APP modified bituminous waterproofing membrane with a thickness of 4 mm. It is reinforced with a non-woven spunbond polyester fabric and is flexible at -10 °C. The top surface is coated with sand, which ensures the bond of the overlying layer. The underside of the product has a burn-off film for easy torch-application.

### USES

The Product is used as a waterproofing membrane for:

- Balconies and terraces under a heavy protection layer such as tiles or gravel.
- Flat and sloped roofs
- Inverted roofs
- Car park decks
- Underground car parks
- Wet areas
- Roads, rail bridges and viaducts
- Basements and other below ground structures
- Horizontal reinforced concrete slabs, decks and podiums
- Vertical reinforced concrete walls

The Product is used as a:

- Base sheet in multi-layer systems
- Single layer under heavy protection

### PRODUCT INFORMATION

<b>Composition</b>	Composition	APP modified bitumen
	Reinforcing material	non-woven spunbond polyester fabric
<b>Packaging</b>	Roll width	1.0 m (EN 1848-1)
	Roll length	8.0 m
Refer to the current price list for available packaging variations.		
<b>Shelf life</b>	36 months from date of production	

### FEATURES

- Very good mechanical properties (tensile, tear, shear)
- High impact resistance
- Easy to install by torching method
- Fully bonded
- Good durability
- Fast and easy installation

### CERTIFICATES AND TEST REPORTS

- CE marking and declaration of performance based on EN 13707:2004+A2:2009 Flexible sheets for waterproofing — Reinforced bitumen sheets for roof waterproofing — Definitions and characteristics
- CE marking and declaration of performance based on EN 14695:2010 Flexible sheets for waterproofing — Reinforced bitumen sheets for waterproofing of concrete bridge decks and other trafficked areas of concrete — Definitions and characteristics

## Storage conditions

The Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +35 °C. Protect the Product from direct weather exposure and sunlight. Store in a vertical position. Pallets may be stacked on top of the rolls if all following conditions are met:

- The rolls have a wooden board on top, separating them from the pallet above.
- The weight of the pallet above is equal to or less than the weight of the rolls.

Always refer to packaging.

<b>Appearance and colour</b>	Top surface	Sand
	Bottom Surface	Polyethylene foil
<b>Thickness</b>	4.0 mm ± 0.3 mm	(EN 1849-1)
<b>Compatibility</b>		

## TECHNICAL INFORMATION

<b>Resistance to static puncture</b>	300N (±15%)	(EN 12730)	
<b>Maximum tensile force</b>	Longitudinal (MD)	1100 N/50 mm ± 220 N/50 mm	(EN 12311-1)
	Transversal (CMD)	900 N/50 mm ± 180 N/50 mm	
<b>Elongation at maximum tensile force</b>	Longitudinal (MD)	50 % ± 15 %	(EN 12311-1)
	Transversal (CMD)	50 % ± 15 %	
<b>Crack bridging ability</b>	Test passed in -10 °C	(EN 14224)	
<b>Joint shear resistance</b>	Longitudinal (MD)	800 N/50 mm ± 160 N/50 mm	(EN 12317-1)
	Transversal (CMD)	600 N/50 mm ± 120 N/50 mm	
<b>Dimensional stability</b>	0.3%	(EN 1107-1)	
	0.3% (in 160 °C)	(EN 14695 / EN 1107-1 Annex. B)	
<b>Service temperature</b>	-20 °C - +70 °C		
<b>Flexibility at low temperature</b>	≤ -10 °C	(EN 1109)	
<b>Flow resistance</b>	130 °C	(EN 1110)	
<b>Water absorption</b>	0.5%	(EN 14223)	
<b>Watertightness</b>	Method B, 24 hours at 60 kPa	Pass (EN 1928)	
<b>Durability</b>	120 °C (Thermal aging behaviour)	(EN 1296 – EN 1110)	
	70 % (Compatibility by Heat Conditions)	(EN 14691)	
	<b>Bonding Resistance in the plane Perpendicular on the surface</b>	EN 14693)	
	At +8°C: 0,7 N/mm <sup>2</sup>		
	At +23°C: 0,5 N/mm <sup>2</sup>		
	<b>Behavior of Bitumen Sheets During Application of Mastic Asphalt</b>	(EN 14693)	
	10mm at -10°C		
	<b>Shear Strength</b>	(EN 13653)	
	0,2 N/mm <sup>2</sup> (Asphalt Concrete)		
	0,3 N/mm <sup>2</sup> (Mastic Asphalt)		
<b>Maximum Temperature of Asphalt Application without Adverse Effects</b>	(EN 13596)		
No adverse effects recorded at +180°C			

## APPLICATION INFORMATION

Ambient air temperature	Maximum	+40 °C
	Minimum	+5 °C
Relative air humidity	Maximum	80 %
Substrate temperature	Maximum	+40 °C
	Minimum	+5 °C

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

#### SYSTEM DESIGN

Consider the following when designing the system:

- The supporting structure must be of sufficient structural strength to support all new and existing layers of the system build-up.
- If used as a roof system, the complete system must be designed to withstand and be secured against wind uplift loadings.

#### SUBSTRATE CONDITION

The substrate surface must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, laitance, oil, dust and loosely adhering particles.

### SUBSTRATE PREPARATION

#### PRIMING

##### Primer selection

Note: For information on selecting the appropriate primer, contact Sika technical service.

1. Apply the appropriate Sika® primer with the required consumption onto the prepared dry surface. Note Refer to the individual Product Data Sheet of the

primer. Primer recommended Sika® Igoflex® P10 GR. Consumption approx. 300 gr/m<sup>2</sup>

2. Allow the primer to dry before membrane installation.

### APPLICATION

#### IMPORTANT

##### Unrolling at low temperatures

At low temperatures, the membrane becomes less flexible.

1. Be careful when unrolling to avoid damaging the membrane.

#### IMPORTANT

##### Damage through footwear

Footwear with spikes or sharp protrusions may puncture the membrane.

1. Use footwear with a flat profile when walking over the membrane.

#### IMPORTANT

##### Damage through overheating

The polyester melts at +260 °C. If it is damaged through overheating, the membrane becomes unusable.

1. Keep moving the flame while torching to avoid overheating the membrane.

#### IMPORTANT

##### Reduced adhesion through insufficient heating

Make sure to heat the membrane sufficiently. If it is not sufficiently heated, the adhesion to the substrate, between layers or on the overlaps will be reduced.

1. If the membrane does not adhere to other elements, lift and retorch the unbonded areas.

#### IMPORTANT

##### Application at less than +5 °C

When applying the membranes at temperatures lower than +5 °C, use heating equipment to ensure that the substrate temperature is within the given temperature range.

#### IMPORTANT

##### Application on sloped surfaces

For slopes with an inclination greater than 15 %, multi-layered roofs must be carefully designed and, if necessary, integrated with mechanical fastenings.

##### Seasonal symbol

Note: If a seasonal symbol is printed on the roll's label, it is advisable to use the membrane during the indicated season.

##### Tackiness at high temperatures

Note: When laying the membrane at high temperatures, the integral adhesive will become 'tacky' and

may restrict laying operations.

#### ALIGNMENT IMPORTANT

##### Avoid coinciding joints

To avoid coinciding joints, lay the membranes parallel to one another. When applying on another bituminous membrane, make sure to straddle the overlaps of the previous layer.

1. Unroll the membrane.
2. Align the membrane.
3. Re-roll the membrane before application.

#### MEMBRANE OVERLAPS

1. Overlap the membranes by a minimum of 100 mm on the sides and 150 mm on each end or as specified by the supplier.
2. At the end overlap, cut off a corner measuring 100 mm per side at an angle of 45°.

#### FASTENING

When used as a roofing sheet, the membrane can be mechanically fixed to the substrate by using the correct type of fasteners.

The number of fixings, type and position depend on wind uplift forces to be resisted, pull-out strength of the fixing screws, the elastic limit of the membrane and the appropriate safety factors.

Contact Sika Technical Service for additional information.

#### Suitable substrates for fastening

- Concrete
- Wood
- Metal
- Perlite screed
- Bituminous membranes
- Coatings (check the compatibility)

#### TORCHING

1. Heat the substrate and the backing film on the underside of the membrane with a gas burner. When the backing film starts to melt, the membrane is ready to stick.
2. Roll the heated membrane forward and press it firmly against the substrate to bond it.
3. Make sure a bead of melted bitumen is visible along the full length of the overlap sides and ends when laying.

#### Suitable substrates for torching

- Concrete
- Perlite screed
- Bituminous membranes with a smooth surface
- Coatings (check the compatibility)
- Brick masonry
- Cementitious screeds

#### DETAILING

1. Use a sharp knife to cut in all details such as internal and external corners, upstands, vent pipes, drains, support metalwork etc.

Refer to the relevant method statement for further in-

formation on detailing.

## MAINTENANCE

Check the functionality of the auxiliary works, flashings, drainage outlets, overflow pipes etc.

Remove any leaves, moss and other vegetation, which could cause ponding on the roof and overload the drainage system.

To maintain the function of the roof waterproofing membrane during its lifespan, it is advisable to arrange periodically for inspection of the membrane and detailing.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika Hellas ABEE

15, Protomagias Str.  
GR 145 68, Kryoneri, Attica  
Tel.: +30 210 81 60 600  
E-mail: info@gr.sika.com  
www.sika.gr



#### Product Data Sheet

SikaShield® P47 S 4 mm  
November 2023, Version 04.01  
020725101000000280

SikaShieldP47S4mm-en-GR-(11-2023)-4-1.pdf