

## PRODUCT DATA SHEET

# SikaRoof® Felt A-200 HF

Non-woven needle-punched polypropylene based geotextile



### DESCRIPTION

SikaRoof® Felt A-200 HF is a 100% virgin high tenacity polypropylene (PP), non-woven needle-punched geotextile.

### USES

SikaRoof® Felt A-200 HF is a non-woven geotextile, UV resistant, used as:

- Separation layer
- Filtration

### CHARACTERISTICS / ADVANTAGES

- 100% polypropylene (PP)
- Bitumen resistant
- Non decaying
- Long lifespan
- Ease of application

### APPROVALS / CERTIFICATES

CE-marking and Declaration of Performance as non-woven needle-punched polypropylene based geotextile, based on 100% polypropylene (PP) according to EN 13249:2016, EN 13250:2016, EN 13251:2016, EN 13252:2016, EN 13253:2016, EN 13254:2016, EN 13255:2016, EN 13256:2016, EN 13257:2016, EN 13265:2016, based on certificate of factory production control issued by notified factory production control certification body and type testing.

### PRODUCT INFORMATION

Composition	Polypropylene
Packaging	Rolls, wrapped individually in PE-foil
Appearance / Colour	White
Shelf life	5 years from date of production
Storage conditions	Product must be stored in dry conditions and temperatures between +5 °C and +30 °C. Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.
Length	50 m (±2 %)
Width	2.2 m (±2 %)
Thickness	With 2kPa load 2.20 mm (±20 %) (EN ISO 9863)

With 20 kPa load	
1.50 mm (±20 %)	(EN ISO 9863)
With 200 kPa load	
0.50 mm (±20 %)	(EN ISO 9863)

<b>Mass per unit area</b>	200 g/m <sup>2</sup> (± 10 %)	(EN ISO 9864)
---------------------------	-------------------------------	---------------

## TECHNICAL INFORMATION

<b>Resistance to static puncture</b>	2.350 N (-10 %) Test CBR	(EN ISO 12236)						
<b>Resistance to dynamic puncture</b>	15,0 mm (± 4,0)	(EN ISO 13433)						
<b>Tensile strength</b>	<table> <tr> <td>Longitudinal</td> <td>14,0 kN/m (-1,9)</td> <td>(EN ISO 10319)</td> </tr> <tr> <td>Transversal</td> <td>16,0 kN/m (- 2,2)</td> <td></td> </tr> </table>	Longitudinal	14,0 kN/m (-1,9)	(EN ISO 10319)	Transversal	16,0 kN/m (- 2,2)		
Longitudinal	14,0 kN/m (-1,9)	(EN ISO 10319)						
Transversal	16,0 kN/m (- 2,2)							
<b>Tensile strain at break</b>	<table> <tr> <td>Longitudinal</td> <td>80 % (±16 %)</td> <td>(EN ISO 10319)</td> </tr> <tr> <td>Transversal</td> <td>80 % (±16 %)</td> <td></td> </tr> </table>	Longitudinal	80 % (±16 %)	(EN ISO 10319)	Transversal	80 % (±16 %)		
Longitudinal	80 % (±16 %)	(EN ISO 10319)						
Transversal	80 % (±16 %)							
<b>Water permeability</b>	Characteristics normal to plane, V <sub>H</sub> 50	77 l/s m <sup>2</sup> (-25) (EN ISO 11058)						
<b>Opening size</b>	Characteristics opening size O <sub>90</sub>	100 µm (±20) (EN ISO 12956)						
<b>Water flow capacity</b>	Water flow in the plane (20 kPa, i=1)	5,0 *10 <sup>-6</sup> m <sup>2</sup> /s (-2,0) (EN ISO 12958)						

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the

product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recom-

mendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Hellas ABEE**

15 Protomagias Str.  
14568 Kryoneri  
Attica-Greece  
Tel.: +30 210 8160 600  
Fax: +30 210 8160 606  
www.sika.gr | sika@gr.sika.com



**Product Data Sheet**

SikaRoof® Felt A-200 HF  
August 2020, Version 03.01  
020945051050000015

SikaRoofFeltA-200HF-en-GR-(08-2020)-3-1.pdf