

# PRODUCT DATA SHEET

## Sika® Plastiment®-15

SUPERPLASTICIZING CONCRETE ADMIXTURE WITH RETARDATION



### DESCRIPTION

Sika® Plastiment®-15 is a multifunctional superplasticizer for concrete.

### USES

- In cases of demands for low water to cement ratio (W/C), increased flow and prolonged workability
- For Ready mix production units
- For concreting under high temperatures
- In cases of fair-faced concrete
- For the production of reduced permeability concrete
- In cases of mass concreting

### CHARACTERISTICS / ADVANTAGES

- Increases workability without increasing mixing water
- Reduces W/C ratio with the same workability
- Increases mechanical strengths
- Improves finishing surface
- Reduces water penetration
- Maintains workability even under difficult circumstances (e.g. high temperature)
- Reduces shrinkage and creep
- Sika® Plastiment®-15 does not contain chloride and is suitable for reinforced and prestressed concrete

### APPROVALS / CERTIFICATES

Set retarding / high range water reducing / super plasticizing admixture (Tables 11.1 & 11.2) according to EN 934.02:2009+A1:2012, Declaration of Performance 92799535, and provided with the CE-mark.

### PRODUCT INFORMATION

<b>Chemical base</b>	Modified, lignosulfonate polymers
<b>Packaging</b>	IBC, 240 kg drums, 20 kg containers. Bulk supply on demand.
<b>Appearance / Colour</b>	Liquid, brown
<b>Shelf life</b>	18 months from date of production
<b>Storage conditions</b>	Store properly in undamaged, unopened, original sealed packaging, in dry conditions at temperatures between +5°C and +35°C. Protect from direct sunlight and frost.
<b>Density</b>	~ 1.19 kg/l (at +20°C)
<b>pH-Value</b>	8.4 -11.4 (at +20°C)
<b>Total Chloride Ion Content</b>	Free (EN 934.01)

## TECHNICAL INFORMATION

---

### Concreting Guidance

The standard rules of good concreting practice, concerning production as well as placing, are to be followed. Refer to relevant standards. Fresh concrete must be cured properly.

---

## APPLICATION INFORMATION

---

### Recommended Dosage

0.2-0.8% by weight of cement  
In normal conditions use 0.2% to 0.5% and for higher demands 0.5% to 0.8%.

---

### Compatibility

Sika® Plastiment®-15 can be combined with the following Sika products:  
- Sika® Plastiment® series  
- Sikament® series  
- Plastocrete® N/ Sika®-1+/ Sika® WT-200 P  
- Sika® Ferrogard®-901 S  
- Sika® Visco I-100  
- Sikafume® HR-E / Sikacrete® AR  
- Sika-Aer® Fine  
Trials are recommended before combining products.

---

### Dispensing

Sika® Plastiment®-15 is added to the gauging water at the plant or added on-site into the concrete mixer.

---

### Restrictions

- When using Sika® Plastiment®-15 a suitable mix design has been taken into account and local material sources should be trialled.
  - Sika® Plastiment®-15 should not be added to dry cement.
  - Sika® Plastiment®-15 should be added with the mixing water or introduced at the end of the mixing process.
  - Before application, suitability tests must be performed.
- 

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Hellas ABEE**  
**15 Protomagias Str.**  
14568 Kryoneri  
Attica-Greece  
Tel.: +30 210 8160 600  
Fax: +30 210 8160 606  
www.sika.gr | sika@gr.sika.com



SikaPlastiment-15\_en\_GR\_(12-2017)\_1\_1.pdf

Product Data Sheet  
Sika® Plastiment®-15  
December 2017, Version 01.01  
021303011000000313