

PRODUCT DATA SHEET

Sikaflex[®]-118 Extreme Grab

CONSTRUCTION ADHESIVE



DESCRIPTION

Sikaflex[®]-118 Extreme Grab is a 1- part, gun applied, phthalate-free adhesive with very high initial grab for bonding onto most common construction substrates. Internal and external use.

USES

An adhesive to bond most construction components and materials such as:

- Concrete
- Masonry
- Most stones
- Ceramic
- Wood
- Metals
- Glass
- Heavy mouldings
- Fibre cement
- Clinker
- Window and door sills

CHARACTERISTICS / ADVANTAGES

- Very high initial grab
- Fixing of heavy objects without temporary fixation
- Good workability
- Very low emissions
- Strong and elastic bond

SUSTAINABILITY

- EMICODE EC1 PLUS
- Class A+ according to French Regulation on VOC emissions

APPROVALS / CERTIFICATES

- CE Mark and Declaration of Performance according to EN 15651-1:2012 - Sealants for exterior and interior application - F EXT-INT CC

PRODUCT INFORMATION

Composition	Silane terminated polymer
Packaging	290 ml cartridge, 12 cartridges per box
Colour	White
Shelf life	12 months from the date of production
Storage conditions	Store in undamaged, original, sealed packaging, in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +25 °C.
Density	~1,40 kg/l (ISO 1183-1)

TECHNICAL INFORMATION

Shore A Hardness	~50 (after 28 d) (ISO 868)
-------------------------	----------------------------

Tensile Strength	~2,2 N/mm ²	(ISO 37)
Elongation at Break	~350 %	(ISO 37)
Tear Propagation Resistance	~10,0 N/mm	(ISO 34)
Service Temperature	-40 °C min. / +80 °C max.	

APPLICATION INFORMATION

Yield	Yield (1 Cartridge 290 ml)	Dimension
	~100 spots	Diameter = 30 mm Thickness = 4 mm
	~5 m bead ^[1]	V-cut nozzle, traingular bead (~60 ml per linear meter)
[1] Note: For heavy objects more or thicker beads up to ~120 ml per linear metre maybe required.		
Sag Flow	0 mm (20 mm profile, 23 °C)	(ISO 7390)
Ambient Air Temperature	+5 °C min. / +40 °C max.	
Substrate Temperature	+5 °C min. / +40 °C max., min. 3 °C above dew point temperature	
Curing Rate	~3 mm/24 h (23 °C / 50 % r.h.)	(CQP 049-2)
	* Sika Corporate Quality Procedure	
Skinning time	~15 min (23 °C / 50 % r.h.)	(CQP 019-1)
	* Sika Corporate Quality Procedure	

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The substrate must be sound, clean, dry and free of all contaminants such as dirt, oil, grease, cement laitance, old sealants and poorly bonded paint coatings which could affect adhesion of the adhesive. For optimum adhesion and critical, high performance applications the following priming and/or pre-treatment procedures shall be followed:

Non-porous substrates

Aluminium, anodised aluminium, stainless steel, galvanised steel, powder coated metals or glazed tiles, slightly roughen surface with a fine abrasive pad. Clean and pre-treat using Sika® Aktivator-205 applied with a clean cloth. Before bonding / sealing, allow a waiting time of

> 15 minutes (< 6 hours). Other metals, such as copper, brass and titanium-zinc, clean and pre-treat using Sika® Aktivator-205 applied with a clean cloth. After a waiting time of > 15 minutes (< 6 hours). Apply Sika® Primer-3 N applied by brush. Allow a further waiting time of > 30 minutes (< 8 hours) before bonding / sealing. PVC has to be cleaned and pre-treated using Sika® Primer-215 applied with a brush. Allow a waiting time of > 15 minutes (< 8 hours) before bonding / sealing.

Porous substrates

Concrete, aerated concrete and cement based renders, mortars and bricks shall be primed using Sika® Primer-3 N applied with a brush. Before bonding, allow a flash-off time of > 30 minutes (< 8 hours). For more detailed advice and instructions please contact Sika Technical Service.

Note: Primers are adhesion promoters and not an al-

ternative to improve poor preparation / cleaning of joint surfaces. Primers also improve the long term adhesion performance of a sealed joint.

APPLICATION METHOD / TOOLS

After the necessary substrate preparation, prepare the end of the cartridge before or after inserting into the sealant gun then fit the nozzle. Apply in triangular beads, strips or spots at intervals of a few centimetres each. Use hand pressure only to fix the components to be bonded into position before skinning of the adhesive occurs. Incorrectly positioned components can easily be unbonded and repositioned during the first few minutes after application. If necessary, use temporary adhesive tapes, wedges, or supports to hold the assembled components together during the initial curing time. Fresh, uncured adhesive remaining on the surface must be removed immediately. Final strength will be reached after complete curing of Sikaflex®-118 Extreme Grab, i.e. after 24 to 48 hours at +23 °C, depending on the environmental conditions and adhesive layer thickness.

CLEANING OF EQUIPMENT

Removal of fresh remnants from tools and application equipment can be carried out using Sika® Remover-208 immediately after use. Hardened / cured material can only be mechanically removed.

FURTHER INFORMATION

- Safety Data Sheet
- Pre-treatment Chart Sealing and Bonding

IMPORTANT CONSIDERATIONS

- For good workability, the adhesive temperature shall be +20 °C.
- Application during high temperature changes is not recommended (movements during the curing).
- Before bonding, check adhesion and resistance of paints and coatings by carrying out a trail.
- Sikaflex®-118 Extreme Grab can be overpainted with most conventional water-based coating and paint systems. However, paints must first be tested to ensure compatibility by carrying out preliminary trials. The best over-painting results are obtained when the adhesive is allowed to fully cure first. Note: non-flexible paint systems may impair the elasticity of the adhesive and lead to cracking of the paint film.
- Colour variations may occur due to exposure to chemicals, high temperatures and/or UV-radiation (especially with the colour shade white). However, a change in colour is purely of aesthetic nature and does not adversely influence the technical performance or durability of the product.
- Always use Sikaflex®-118 Extreme Grab in conjunction with mechanical fixings for overhead applications of heavy items.
- For very heavy items provide temporary support until Sikaflex®-118 Extreme Grab has fully cured.
- Full surface applications / bondings are not recommended since the inner part of the adhesive layer may never cure.
- Before using Sikaflex®-118 Extreme Grab on natural stone, contact Sika Technical Service.
- Do not use Sikaflex®-118 Extreme Grab on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might bleed oils, plasticizers or solvents that could attack the adhesive.
- Do not use Sikaflex®-118 Extreme Grab on polyethylene (PE), polypropylene (PP), polytetrafluoroethylene (PTFE / Teflon), and certain plasticized synthetic materials (pre-trials shall be carried out or contact Sika Technical Service).
- Do not use Sikaflex®-118 Extreme Grab for glass bonding if the bond line is exposed to sunlight.
- Do not use Sikaflex®-118 Extreme Grab for structural bonding.
- Do not expose uncured Sikaflex®-118 Extreme Grab to alcohol containing products as this may interfere with the curing reaction.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may

vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Hellas ABEE
15 Protomagias Str.
14568 Kryoneri
Attica-Greece
Tel.: +30 210 8160 600
Fax: +30 210 8160 606
www.sika.gr | sika@gr.sika.com



Product Data Sheet
Sikaflex®-118 Extreme Grab
May 2019, Version 04.01
02051302000000046

Sikaflex-118ExtremeGrab-en-GR-(05-2019)-4-1.pdf

