

## PRODUCT DATA SHEET

# SikaShield® P34 MG RO 4,5 kg/m<sup>2</sup>

Plastomeric bituminous membrane surfaced with mineral granules and flexible at -5 °C

### DESCRIPTION

SikaShield® P34 MG RO 4,5 kg/m<sup>2</sup> is an APP modified bituminous roof waterproofing membrane with a weight of 4,5 kg/m<sup>2</sup>. It is reinforced with a non-woven polyester fabric and is flexible at -5 °C. The top surface is coated with mineral granules, which allows the permanent exposure to UV radiation. The underside of the product has a burn-off film for easy torch-application.

### USES

The Product is used as a waterproofing membrane for:

- Balconies
- Flat roofs

The Product is used as a:

- Exposed cap sheet in a multi-layer system

### FEATURES

- Decorative mineral granules
- Can be painted immediately after application
- Easy to install by torching method
- Flexible in cold temperatures
- Fully bonded
- Good mechanical properties (tensile, tear, shear)

### CERTIFICATES AND TEST REPORTS

- CE marking and declaration of performance based on EN 13707:2004+A2:2009 Flexible sheets for waterproofing — Reinforced bitumen sheets for roof waterproofing — Definitions and characteristics

### PRODUCT INFORMATION

<b>Composition</b>	Composition	APP modified bitumen
	Reinforcing material	non-woven polyester fabric
<b>Packaging</b>	Roll width	1.0 m (EN 1848-1)
	Roll length	10.0 m
Refer to the current price list for available packaging variations.		
<b>Shelf life</b>	36 months from date of production	
<b>Storage conditions</b>	<p>The Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +35 °C. Protect the Product from direct weather exposure and sunlight. Store in a vertical position. Pallets may be stacked on top of the rolls if all following conditions are met:</p> <ul style="list-style-type: none"> <li>▪ The rolls have a wooden board on top, separating them from the pallet above.</li> <li>▪ The weight of the pallet above is equal to or less than the weight of the rolls.</li> </ul> <p>Always refer to packaging.</p>	

<b>Appearance and colour</b>	Top surface	Mineral Granules
	Bottom Surface	Polyethylene foil
	Top layer colour	Refer to current price list for color variations
<b>Mass per area</b>	Mass per unit area	4.5 kg/m <sup>2</sup> ± 0.45 kg/m <sup>2</sup> (EN 1849-1)

## TECHNICAL INFORMATION

<b>Maximum tensile force</b>	Longitudinal (MD)	480 N/50 mm ± 96 N/50 mm	(EN 12311-1)
	Transversal (CMD)	350 N/50 mm ± 70 N/50 mm	
<b>Elongation at maximum tensile force</b>	Longitudinal (MD)	35 % ± 15 %	(EN 12311-1)
	Transversal (CMD)	35 % ± 15 %	
<b>Flexibility at low temperature</b>	≤ -5 °C		(EN 1109)
<b>Watertightness</b>	Method B, 24 hours at 60 kPa	Pass	(EN 1928)
<b>Reaction to fire</b>	Class E		(EN 13501-1)

## APPLICATION INFORMATION

<b>Ambient air temperature</b>	Maximum	+40 °C
	Minimum	+5 °C
<b>Relative air humidity</b>	Maximum	80 %
<b>Substrate temperature</b>	Maximum	+40 °C
	Minimum	+5 °C

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

### Application of torch-applied membranes

Note: Always make reference to local regulations, standards, guidelines and established practice when using torch-applied membranes.

- Method Statement - Roofing build-up with bituminous membranes

## ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this

product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

#### SYSTEM DESIGN

Consider the following when designing the system:

- The supporting structure must be of sufficient structural strength to support all new and existing layers of the system build-up.
- If used as a roof system, the complete system must be designed to withstand and be secured against wind uplift loadings.

#### SUBSTRATE CONDITION

The substrate surface must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, laitance, oil, dust and loosely adhering particles.

## SUBSTRATE PREPARATION

### PRIMING

#### Primer selection

Note: For information on selecting the appropriate primer, contact Sika technical service.

1. Apply the appropriate Sika® primer with the required consumption onto the prepared dry surface.

Note: Refer to the individual Product Data Sheet of the primer. Primer recommended Sika® Igoflex® P10 GR. Consumption approx. 300gr/m<sup>2</sup>.

2. Allow the primer to dry before membrane installation.

## MAINTENANCE

Check the functionality of the auxiliary works, flashings, drainage outlets, overflow pipes etc.

Remove any leaves, moss and other vegetation, which could cause ponding on the roof and overload the drainage system.

To maintain the function of the roof waterproofing membrane during its lifespan, it is advisable to arrange periodically for inspection of the membrane and detailing.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika Hellas ABEE

15, Protomagias Str.  
GR 145 68, Kryoneri, Attica  
Tel.: +30 210 81 60 600  
E-mail: info@gr.sika.com  
www.sika.gr



#### Product Data Sheet

SikaShield® P34 MG RO 4,5 kg/m<sup>2</sup>  
November 2023, Version 02.01  
020920011990001838

SikaShieldP34MGRO45kgm-en-GR-(11-2023)-2-1.pdf