

PRODUCT DATA SHEET

Sikatherm® EPS 150

FLAME RETARDANT, EXPANDED POLYSTYRENE BOARDS (EPS) WITH HIGH THERMAL INSULATION PROPERTIES



DESCRIPTION

Sikatherm® EPS 150 are boards of expanded polystyrene with high thermal insulating properties, which remain unaffected in time.

USES

Thermal insulation underneath waterproofing layer in following roofing system structures:

- Sarnafil® S 327, TS 77 mechanically fastened single ply membrane systems
- Sikaplan® G, VG, VGWT, TM mechanically fastened single ply membrane systems
- Sarnafil® G 410, TG 66 loose laid ballast membrane systems
- Sikaplan® SGmA, TB loose laid ballast membrane systems

CHARACTERISTICS / ADVANTAGES

- Homogeneity of the physical and mechanical characteristics of the product and therefore isotropical behaviour
- Stability against tension, distortion, break, degradation and ageing
- Ideal for new constructions and refurbishment projects
- Lightweight, applying thus low load on the roofing structure
- 100% recyclable

APPROVALS / CERTIFICATES

CE-marking and Declaration of Performance as Thermal insulation product for buildings – Factory made expanded polystyrene (EPS) with self-extinguishing properties according to EN 13163:2012 based on certificate of constancy of performance of the construction product issued by notified product certification body.

PRODUCT INFORMATION

Composition	EPS
Packaging	Boards individually wrapped with polyethylene sheet.
Colour	White
Shelf life	Unlimited if storage conditions are met.
Storage conditions	The packaging of Sikatherm® EPS 150 shall not be considered adequate for long term outside protection. Ideally, boards shall be stored inside a building. If however, outside storage cannot be avoided the boards shall be stacked clear of the ground and covered with a polythene sheet or weatherproof tarpaulin.

Dimensions	2500 mm x 1000 mm (EN13163) Other dimensions available following special order request Thickness tolerance (T): ± 2 (EN 822) Length tolerance (L): ± 3 (EN 822) Width tolerance (W): ± 3 (EN 822) Squareness tolerance (S): ± 5 (EN 825) Flatness tolerance (P): ± 10 (EN 824)
Thickness	20 - 300 mm

TECHNICAL INFORMATION

Compressive Strength	≥ 150 kPa at 10% deformation [CS(10)]	(EN 826)																																						
Tensile Strength in Flexure	≥ 200 kPa	(EN 12090)																																						
Dimensional Stability	DS(N) $\leq 2\%$	(EN 1603)																																						
Reaction to Fire	Class E	(EN 13501-1)																																						
Thermal Conductivity	$\lambda_d = 0,034$ W/m K	(EN 12667)																																						
Thermal Resistance	<table border="1"> <thead> <tr> <th>Thickness</th> <th>$R_d = [m^2 K/W]$</th> </tr> </thead> <tbody> <tr><td>20</td><td>0,588</td></tr> <tr><td>30</td><td>0,882</td></tr> <tr><td>40</td><td>1,176</td></tr> <tr><td>50</td><td>1,471</td></tr> <tr><td>60</td><td>1,765</td></tr> <tr><td>70</td><td>2,059</td></tr> <tr><td>80</td><td>2,353</td></tr> <tr><td>100</td><td>2,941</td></tr> <tr><td>120</td><td>3,529</td></tr> <tr><td>140</td><td>4,118</td></tr> <tr><td>160</td><td>4,706</td></tr> <tr><td>180</td><td>5,294</td></tr> <tr><td>200</td><td>5,882</td></tr> <tr><td>220</td><td>6,471</td></tr> <tr><td>240</td><td>7,059</td></tr> <tr><td>260</td><td>7,647</td></tr> <tr><td>280</td><td>8,235</td></tr> <tr><td>300</td><td>8,824</td></tr> </tbody> </table>	Thickness	$R_d = [m^2 K/W]$	20	0,588	30	0,882	40	1,176	50	1,471	60	1,765	70	2,059	80	2,353	100	2,941	120	3,529	140	4,118	160	4,706	180	5,294	200	5,882	220	6,471	240	7,059	260	7,647	280	8,235	300	8,824	(EN 12667)
Thickness	$R_d = [m^2 K/W]$																																							
20	0,588																																							
30	0,882																																							
40	1,176																																							
50	1,471																																							
60	1,765																																							
70	2,059																																							
80	2,353																																							
100	2,941																																							
120	3,529																																							
140	4,118																																							
160	4,706																																							
180	5,294																																							
200	5,882																																							
220	6,471																																							
240	7,059																																							
260	7,647																																							
280	8,235																																							
300	8,824																																							

Diffusion Resistance to Water Vapour	30-70	(EN 12086)
Permeability to Water Vapour	0,009 – 0,020 mg/(Pa·h·m)	(EN 12086)

SYSTEMS

System Structure	<p>Ancillary products and system components according to local price list.</p> <p>Roof waterproofing singly ply membranes :</p> <ul style="list-style-type: none"> ▪ Sarnafil® TS, TG, G ▪ Sikaplan® G, VG, VGWT, SGmA, SGK, TM, TB <p>Fasteners and fixings:</p> <ul style="list-style-type: none"> ▪ Sarnafast® range <p>Vapour control layers:</p> <ul style="list-style-type: none"> ▪ Sarnavap® range <p>Separation layer with PVC membranes:</p> <ul style="list-style-type: none"> ▪ SikaRoof® Felt product range, polyester or polypropylene based, > 300gr/m² ▪ S-Glass Fleece-120
-------------------------	---

Compatibility

Sikatherm® EPS 150 is compatible with FPO and PVC single ply membranes Sikaplan® / Sarnafil®.

No additional separation layer is required, when TPO based Sikaplan®/Sarnafil® is applied over the board surface.

When PVC based Sikaplan® / Sarnafil® is applied over the board surface, SikaRoof® Felt >300gr/m² geotextile or S-Glass Fleece-120 has to be installed.

APPLICATION INFORMATION

Ambient Air Temperature

Limited to appropriate roof waterproofing membrane system temperature limitations. Please refer to the respective Product Data Sheets.

Substrate Temperature

Limited to appropriate roof waterproofing membrane system temperature limitations. Please refer to the respective Product Data Sheets.

APPLICATION INSTRUCTIONS

APPLICATION METHOD / TOOLS

Sikatherm® EPS 150 is installed by mechanical attachment, over suitable Vapour Control Layer, to the roof deck with Sarnafast fasteners. The minimum fasteners' number required is one per m² of thermal insulation. The requirements for securing the waterproofing membrane shall be considered separately. The detailed fastening system of the thermal insulation shall be considered separately for each project according to local requirements. In ballasted roof the boards are loose laid. The specified ballast should be installed as soon as possible, once the waterproofing membrane has been installed. Mechanical fixation can also be used for the thermal insulation in ballasted roof systems.

IMPORTANT CONSIDERATIONS

- Installation works to be carried out only by Sika instructed contractors for roofing.
- Temperature limits will depend on waterproofing membrane installation limits. Use of some ancillary products, e.g. adhesives is limited to temperatures above +5 °C. Please refer to the respective Product Data Sheets.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in this product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0.1% (w/w).

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product

Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Hellas ABEE
15 Protomagias Str.
14568 Kryoneri
Attica-Greece
Tel.: +30 210 8160 600
Fax: +30 210 8160 606
www.sika.gr | sika@gr.sika.com



Product Data Sheet
Sikatherm® EPS 150
April 2020, Version 01.01
02093503100000002

SikathermEPS150-en-GR-(04-2020)-1-1.pdf

