

## SYSTEM DATA SHEET

# Sikafloor® MultiDur EB-27 ECC

SLIP RESISTANT BROADCAST COLOURED EPOXY FLOOR SYSTEM FOR DAMP SUBSTRATES.

## DESCRIPTION

Sikafloor® MultiDur EB-27 ECC is a 2-part epoxy coloured resin based flooring system that can provide a hard wearing, seamless, low maintenance, slip resistant finish when broadcast with different aggregate grades. For damp substrates and medium - heavy wear conditions. Thickness 4,0–6,0 mm. Internal use

## USES

Sikafloor® MultiDur EB-27 ECC may only be used by experienced professionals.

- On concrete and cementitious screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages and loading ramps.
- On multi-storey and underground car park decks and for wet process areas, e.g. beverage and food industry

## CHARACTERISTICS / ADVANTAGES

- Seamless
- High wear resistance
- Good chemical and mechanical resistance
- Easy application
- Waterproof
- Gloss finish
- Slip resistant
- Low maintenance
- Good bond to green or hardened damp/dry concrete

## SUSTAINABILITY

- Conformity with LEED v4 MRc 2 (Option 1): Building Product Disclosure and Optimization – Environmental Product Declarations
- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients


## APPROVALS / CERTIFICATES

- CE Marking and Declaration of Performance to EN 1504-2 - Surface protection product for concrete - Coating
- CE Marking and Declaration of Performance to EN 13813 - Resin screed material for internal use in buildings
- Particle emission ISO 14644-1, CSM Statement of Qualification, Fraunhofer IPA Report No. SI 1709-952
- Outgassing behavior VOC/SVOC ISO 14644-8, CSM Statement of Qualification, Fraunhofer IPA, Report No. SI 1709-952
- Indirect contact to foodstuff (EU) 1935/2004, Sikafloor®-264 N Sikafloor®-264 N LO, Fesenius Bericht, Test report No. 3419034-01
- VOC emission, Sikafloor®-264 N, CSM Fraunhofer, Certificate No. SI 1709-952
- Particle emission ISO 14644-1, CSM Statement of Qualification, Fraunhofer IPA Report No. SI 1709-952

# SYSTEMS

## System Structure

### Sikafloor® MultiDur EB-27 ECC (~ 4–6 mm)



Layer	Product
1. Primer	Sikafloor®-155 WN
2. Levelling screed	Sikafloor®-81 EpoCem®
3. Wearing finish	Sikafloor®-263 SL N + aggregate broadcast quartz sand 0,3–0,8 mm
4. Seal / Top coat	Sikafloor®-264 N

Composition	Epoxy
Appearance	Slip resistant gloss finish
Colour	Available in many colours
Nominal Thickness	~ 4–6 mm

## TECHNICAL INFORMATION

Abrasion Resistance	~41 mg (CS 10/1000/1000) (8 days / +23 °C)	(DIN 53 109 Taber Abraser Test)
Compressive Strength	~60 N/mm <sup>2</sup> ( 28 days at 23 °C / 50 % R.H.)	(EN 13892-2)
Tensile Strength	~14 N/mm <sup>2</sup> (28 days at 23 °C / 50 % R.H.)	(EN 13892-2)
Tensile Adhesion Strength	> 1,5 N/mm <sup>2</sup> (failure in concrete)	(ISO 4624)
Chemical Resistance	Resistant to many chemicals. Contact Sika Technical Service for specific information.	
Coefficient of Friction	μ = 0,54	(DIN 51131)
Skid / Slip Resistance	R11 V4	(DIN 51130)

## APPLICATION INFORMATION

<b>Consumption</b>	Sikafloor® MultiDur EB-27 ECC (~ 4 – 6mm)			
	<b>Layer</b>	<b>Product</b>	<b>Consumption</b>	
	1. Primer	1 × Sikafloor®-155 WN	~0,3–0,5 kg/m <sup>2</sup> thinned with 10 % water	
	2. Levelling screed	1 × Sikafloor®-81 Epo-Cem®	~2,25 kg/m <sup>2</sup> /mm	
	3. Wearing layer	1 × Sikafloor®-263 SL N filled 1:1 with quartz sand 0,1–0,3 mm	~ 4 kg/m <sup>2</sup> (2 kg/m <sup>2</sup> resin + 2 kg/m <sup>2</sup> quartz sand) for 2 mm film thickness	
	4. Sand broadcast	Quartz Sand 0,3–0,8 mm	~ 4–6 kg/m <sup>2</sup>	
	5. Seal / Top coat	1–2 × Sikafloor®-264 N	~0,6–0,8 kg/m <sup>2</sup>	
<b>Ambient Air Temperature</b>	+10 °C min / +30 °C max			
<b>Relative Air Humidity</b>	80 % r.h. max.			
<b>Dew Point</b>	Beware of condensation! The substrate and uncured floor temperature must be at least 3 °C above the dew point to reduce the risk of condensation or blooming on the floor finish.			
<b>Substrate Temperature</b>	+10 °C min. / +30 °C max.			
<b>Substrate Moisture Content</b>	Can be applied on green or damp concrete with no standing water. Although the system can be applied onto green concrete surfaces (> 24 hours), it is advised to allow at least 3 days for early concrete shrinkage to occur in order to prevent shrinkage cracks from appearing on the wearing surface.			
<b>Waiting Time / Overcoating</b>	Before applying Sikafloor®-81 EpoCem® on Sikafloor®-155 WN allow:			
	<b>Substrate Temperature</b>	<b>Minimum</b>	<b>Maximum</b>	
	+10 °C	12 hours	72 hours	
	+20 °C	6 hours	48 hours	
	+30 °C	4 hours	24 hours	
	Sikafloor®-81 EpoCem® can be overcoated with vapour impermeable coatings when the surface humidity falls below 4 %.			
	Not earlier than :			
	<b>Substrate Temperature</b>	<b>Waiting Time</b>		
	+10 °C	2 days		
	+20 °C	1 day		
	+30 °C	1 day		
	Before applying Sikafloor®-264 N on Sikafloor®-263 SL N allow:			
	<b>Substrate Temperature</b>	<b>Minimum</b>	<b>Maximum</b>	
	+10 °C	30 hours	72 hours	
	+20 °C	24 hours	48 hours	
	+30 °C	16 hours	24 hours	
	Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity			
<b>Applied Product Ready for Use</b>	<b>Temperature</b>	<b>Foot traffic</b>	<b>Light traffic</b>	<b>Full cure</b>
	+10 °C	~ 72 hours	~ 6 days	~ 10 days
	+20 °C	~ 24 hours	~ 4 days	~ 7 days
	+30 °C	~ 18 hours	~ 2 days	~ 5 days

## PRODUCT INFORMATION

**Packaging** Refer to the individual Product Data Sheet

**Shelf life** Refer to the individual Product Data Sheet

**Storage conditions** Refer to the individual Product Data Sheet

## MAINTENANCE

### CLEANING

Refer to the Method Statement Sikafloor®-Cleaning Regime

### FURTHER INFORMATION

- Sika® Method Statement Mixing & Applications of Flooring systems
- Sika® Method Statement Evaluation and Preparation of Surfaces for Flooring systems

### IMPORTANT CONSIDERATIONS

- Sikafloor®-155 WN and Sikafloor®-81 Epo-Cem®: Refer to individual product limitations.
- Freshly applied Sikafloor® MultiDur EB-27 ECC must be protected from damp, condensation and water for at least 24 hours.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- For exact colour matching, ensure the Sikafloor®-264 N in each area is applied from the same control batch numbers.
- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to indentations in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO<sub>2</sub> and H<sub>2</sub>O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

### BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika Hellas ABEE

15 Protomagias Str.  
14568 Kryoneri  
Attica-Greece  
Tel.: +30 210 8160 600  
Fax: +30 210 8160 606  
www.sika.gr | sika@gr.sika.com



#### System Data Sheet

Sikafloor® MultiDur EB-27 ECC  
April 2020, Version 02.01  
02081190000000090

SikafloorMultiDurEB-27ECC-en-GR-(04-2020)-2-1.pdf