

# PRODUCT DATA SHEET

## Sikagard®-403 W

SINGLE COMPONENT, WATERBORNE, MODIFIED ACRYLIC RESIN WALL COATING

### DESCRIPTION

Sikagard®-403 W is a single component, waterborne modified acrylic resin based intermediate and surface coating, containing an antimicrobial additive.

### USES

Sikagard®-403 W may only be used by experienced professionals.

- Application on concrete, bricks, cement and gypsum based substrates, metal surfaces, timber, tiles and plastic
- Embedment, intermediate and top coat for internal walls and ceilings
- Suitable for production facilities in the pharmaceutical, medical engineering, food and beverage industry, as well as, hospitals, prisons, healthcare and leisure facilities

### CHARACTERISTICS / ADVANTAGES

- Seamless, easy to clean finish
- Good resistance to repeated cleaning regimes using mild detergents and cleaning solutions
- Tough and highly durable
- Good water vapour permeability
- More flexible in comparison to standard acrylic paints, improves resistance to cracking and flaking
- Ultra-low emissions
- Good opacity
- Odourless
- Easy to apply

### SUSTAINABILITY

Conformity with LEED v2009 IEQc 4.2: Low-Emitting Materials - Paints and Coatings

### APPROVALS / CERTIFICATES

- Eurofins, test report No. 392-2014-0027 0301, VOC emission acc. French Regulations Decret DEVL 11019093D, March 23, 2011 and Decret DEVL 11034675A, February 15, 2016.
- PRA, test report No. 77388-004, gloss, fineness, grind wet scrub resistance and contrast ratio according to EN 13300, September 30, 2014.
- Exova Warringtonfire, test report No. WF 343711, classification reaction to fire according to EN 13501-1:2007+A1:2009, September 15, 2014.
- IMSL, test report No. 2014/02/011.1A-1, determination of antibacterial activity according to ISO 22196, December 29th 2014.
- IMSL, test report No. 2014/12/009.2A, determination of resistance of surface coatings to mould growth according to BS 3900, Part G6, April 21, 2015
- 4wardtesting, test report No. C2882, water vapour transmission rate and water vapour permeability according to ISO 7783-1:2000 (superseded by EN ISO 7783:2011, November 30, 2011), August 29, 2014.
- Eurofins, test report No. 392-2015-00292201, determination of VOC and SVOC content according to ISO 11890-2, CEPE/EC/2015-04-13 and Commission Decision 2014/312/EU, October 6, 2015
- KIWA GmbH Polymer Institute, test report P10108-E, determination of crack bridging properties according to DIN EN 1062-7, April 12, 2016
- Campden BRI Group, test report No. S/REP/139540/1 Sensory Evaluation of the Taint Potential, Triangle Test Method TES -S-002, Odour Transfer Method, July 15, 2016

## PRODUCT INFORMATION

<b>Chemical base</b>	Styrene-acrylic Copolymer Dispersion, waterborne
<b>Packaging</b>	5.0 l = 6.60 kg drums 15.0 l = 19.80 kg drums
<b>Appearance / Colour</b>	white pastel colour shades on request
<b>Shelf life</b>	12 month from date of production
<b>Storage conditions</b>	Store in closed, sealed and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight and frost.
<b>Density</b>	~ 1.34 kg/l (+23°C) (EN ISO 2811-1)
<b>Solid content by weight</b>	~61%
<b>Solid content by volume</b>	~47%

## TECHNICAL INFORMATION

<b>Tensile Strength</b>	~ 2.8 N/mm <sup>2</sup> unreinforced	(EN ISO 527-3)																				
<b>Elongation at Break</b>	~ 90 % unreinforced	(EN ISO 527-3)																				
<b>Tensile Adhesion Strength</b>	> 1.5 N/mm <sup>2</sup> to concrete primed with Sika Bonding Primer	ISO 4624																				
<b>Chemical Resistance</b>	Resistant to mild detergents and cleaning agents. Please contact Sika technical service for specific information. Disinfection with Hydrogen Peroxide Vapour: <ul style="list-style-type: none"><li>▪ Resistant when using Steris VHP technology</li><li>▪ Resistant to PEA vaporisation technology, when a system build up with glass fibre reinforcement is used</li><li>▪ Resistant when using Oxypharm vaporiser type NOCOSPRAY under following conditions:</li></ul>																					
	<table><thead><tr><th>Disinfectant</th><th>Concentration</th><th>Setting at vaporiser</th><th>Contact time</th></tr></thead><tbody><tr><td>NOCOLYSE Mint (6 %)</td><td>1 ml/m<sup>3</sup></td><td>20 m<sup>3</sup> (1.5 minutes vaporisation)</td><td>30 min</td></tr><tr><td>NOCOLYSE One Shot (12 %)</td><td>3 ml/m<sup>3</sup> (2 cycles)</td><td>45m<sup>3</sup> (5 minutes vaporisation)</td><td>30 min</td></tr><tr><td>NOCOLYSE Food (7.9 %)</td><td>1 ml/m<sup>3</sup></td><td>20 m<sup>3</sup> (1.5 minutes vaporisation)</td><td>30 min</td></tr><tr><td>NOCOLYSE Food (7.9 %)</td><td>5 ml/m<sup>3</sup> (2 cycles)</td><td>75m<sup>3</sup> (5 minutes vaporisation)</td><td>60 min</td></tr></tbody></table>	Disinfectant	Concentration	Setting at vaporiser	Contact time	NOCOLYSE Mint (6 %)	1 ml/m <sup>3</sup>	20 m <sup>3</sup> (1.5 minutes vaporisation)	30 min	NOCOLYSE One Shot (12 %)	3 ml/m <sup>3</sup> (2 cycles)	45m <sup>3</sup> (5 minutes vaporisation)	30 min	NOCOLYSE Food (7.9 %)	1 ml/m <sup>3</sup>	20 m <sup>3</sup> (1.5 minutes vaporisation)	30 min	NOCOLYSE Food (7.9 %)	5 ml/m <sup>3</sup> (2 cycles)	75m <sup>3</sup> (5 minutes vaporisation)	60 min	
Disinfectant	Concentration	Setting at vaporiser	Contact time																			
NOCOLYSE Mint (6 %)	1 ml/m <sup>3</sup>	20 m <sup>3</sup> (1.5 minutes vaporisation)	30 min																			
NOCOLYSE One Shot (12 %)	3 ml/m <sup>3</sup> (2 cycles)	45m <sup>3</sup> (5 minutes vaporisation)	30 min																			
NOCOLYSE Food (7.9 %)	1 ml/m <sup>3</sup>	20 m <sup>3</sup> (1.5 minutes vaporisation)	30 min																			
NOCOLYSE Food (7.9 %)	5 ml/m <sup>3</sup> (2 cycles)	75m <sup>3</sup> (5 minutes vaporisation)	60 min																			
<b>Permeability to Water Vapour</b>	~ 37.5 g/m <sup>2</sup> in 24 hours	EN ISO 7783-1																				

## APPLICATION INFORMATION

<b>Consumption</b>	~ 0.28 kg/m <sup>2</sup> per layer unreinforced ~ 0.80 kg/m <sup>2</sup> per layer for reinforcement with Sika Reemat Premium	
<b>Layer Thickness</b>	wet film thickness	~ 200 µm per layer unreinforced
	dry film thickness	~ 100 µm per layer unreinforced
<b>Product Temperature</b>	+8 °C min. / +35 °C max.	
<b>Ambient Air Temperature</b>	+8 °C min. / +35 °C max.	
<b>Relative Air Humidity</b>	< 80%	

<b>Dew Point</b>	Beware of condensation! Substrate temperature must be at least +3 °C above dew point.		
<b>Substrate Temperature</b>	+8 °C min. / +35 °C max.		
<b>Substrate Moisture Content</b>	Visible damp free		
<b>Curing Time</b>	Before overcoating with Sikagard®-403 W		
	<b>Temperature</b>	<b>Minimum</b>	<b>Maximum</b>
	+10°C	4 hours	7 days
	+20°C	2 hours	7 days
	+30°C	1 hour	7 days
	Before overcoating with 2-comp. top coats		
	<b>Temperature</b>	<b>Minimum</b>	<b>Maximum</b>
	+10°C	16 hours	7 days
	+20°C	8 hours	7 days
	+30°C	4 hours	7 days

## APPLICATION INSTRUCTIONS

Stir product mechanically until a uniform liquid has been achieved.

Use a low speed electrical stirrer (300-400 rpm) to avoid air entrapment.

For roller application use short piled roller. For airless application use tip sizes from 0.38 to 0.53mm/ angle 40° to 60°.

### CLEANING OF TOOLS

Removal of fresh remnants from tools and application equipment can be carried out using water immediately after use. Hardened and/or cured material can only be removed mechanically.

### LIMITATIONS

- Each type of roller will give a slightly different surface finish – always use same roller type in same areas.
- Airless spray will lead to a surface smoother than roller applied areas, use same application type in same areas.
- When applied with Sika Reemat Premium a slight surface texture will stay visible.
- Ensure entire surface is fully dried before over coating.
- Crazeing may occur when over coating un-dried areas.
- Always ensure good ventilation when application takes place in a confined space to ensure drying.
- The incorrect treatment of cracks may lead to a reduced service life and reflective cracking.
- Do not apply near foodstuffs in unventilated conditions, always ensure ventilation.
- Acoustic insulation boards may lose some acoustic absorption properties.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control. All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary

due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

### DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type wb) is 140 g/l (Limits 2010) for the ready to use product.

The maximum content of Sikagard®-403 W is <140 g/l VOC for the ready to use product.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its

products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Hellas ABEE**  
**15 Protomagias Str.**  
14568 Kryoneri  
Attica-Greece  
Tel.: +30 210 8160 600  
Fax: +30 210 8160 606  
[www.sika.gr](http://www.sika.gr) | [sika@gr.sika.com](mailto:sika@gr.sika.com)



Sikagard-403W\_en\_GR\_(08-2017)\_4\_1.pdf

Product Data Sheet  
Sikagard®-403 W  
August 2017, Version 04.01  
020813020020000013