

PRODUCT DATA SHEET

Sika[®] Reactivation Primer

One-component primer for reactivation of the existing Sikalastic[®] waterproofing systems

DESCRIPTION

Sika[®] Reactivation Primer is a one-component polyurethane based primer for the reactivation of SikaRoof[®] MTC, Sikalastic[®] roofing systems and Sikafloor[®] balcony waterproofing systems.

USES

Primer for use when recoating existing:

- SikaRoof[®] MTC
- Sikalastic[®] roofing systems
- Sikafloor[®] balcony waterproofing systems.

FEATURES

- One-component, easy and ready to use
- Enhances adhesion to existing Sikalastic[®] and Sikafloor[®] systems
- Allows further coats to be safely applied when the standard re-coating window has been exceeded
- Suitable for use over a wide range of existing polyurethane roofing membranes (subject to satisfactory adhesion testing)

PRODUCT INFORMATION

Composition	Solvent borne polyurethane
Packaging	5.0 lt (~5.15 kg) metal container
Shelf life	12 months from date of production
Storage conditions	The product must be stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between 0 °C and +25 °C. Higher storage temperatures may reduce shelf life of product. Reference shall also be made to the storage recommendations within the safety data sheet.
Appearance and colour	Low viscosity liquid, clear
Density	~1.03 kg/lt (at 23 °C)

APPLICATION INFORMATION

Consumption	Apply in 1 coat, with a consumption of 0.10 kg/m ² approx.	
Ambient air temperature	Minimum	+5 °C
	Maximum	+30 °C
Relative air humidity	85 % r.h. max.	

Dew point	Beware of condensation. The substrate and uncured membrane must be at least 3 °C above dew point to reduce the risk of condensation or blooming of the membrane finish.	
Substrate temperature	Minimum	+5 °C
	Maximum	+30 °C
Pot Life	Once opened, the product should be used promptly. Storage of partial containers may result in performance being affected.	
Waiting time to overcoating	Temperature	Waiting time
	5 °C	5–6 hours
	20 °C	3–4 hours
Sika® Reactivation Primer can be overcoated once cured and tack free. Maximum recoat period within 48 hours of application of the primer. Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.		

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Do not apply in wet weather or to wet surfaces
- Take care to ensure an even coverage and avoid ponding in voids and depressions
- Do not apply close to the air intake vent of a running air conditioning unit

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

Regulation (EC) No 1907/2006 (REACH) - Mandatory training

As from 24 August 2023 adequate training is required before industrial or professional use of this product. For more information and a link to the training visit www.sika.com/pu-training.



APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The surfaces must be clean, dry, free of stripping agents and free of oil, grease, silanes, salts, silicone, siloxanes and other chemicals which could cause poor adhesion.

SUBSTRATE PREPARATION

All surfaces to be coated should be thoroughly cleaned by conventional means. Pre-treat with Sika® Biowash on areas subject to organic growth.

If in doubt, apply a test area first.

For detailed information regarding substrate quality/preparation and primer chart, please refer to the Method of Statement.

APPLICATION

Prepare Sika® Reactivation Primer by stirring thoroughly.

Sika® Reactivation Primer can be applied by short-piled roller or brush.

Allow Sika® Reactivation Primer to dry sufficiently (see table waiting time/overcoating) before overcoating.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Hellas ABEE

15, Protomagias Str.
GR 145 68, Kryoneri, Attica
Tel.: +30 210 81 60 600
E-mail: info@gr.sika.com
www.sika.gr



Product Data Sheet

Sika® Reactivation Primer
August 2024, Version 04.01
020915951000000008

SikaReactivationPrimer-en-GR-(08-2024)-4-1.pdf