



SIKA
MARINE



THE
PROFESSIONAL'S
CHOICE

Sikaflex[®]-295 UV SEAL LIKE A PRO

- Sealant for organic glass, hatches and deck edges
- Outstanding UV Stability
- Resistant to ageing and weathering

BUILDING TRUST



Sikaflex[®]-295 UV

HIGH PERFORMANCE UV RESISTANT SEALANT FOR SKIN FITTINGS, ORGANIC GLASS WINDOWS, HATCHES AND DECK EDGES

Sikaflex[®]-295 UV is a 1-component polyurethane adhesive that cures on exposure to atmospheric moisture. It is suitable for interior and exterior sealing applications and to bond organic glass in the Marine business. Sikaflex[®]-295 UV meets the requirements set out by the International Maritime Organization (IMO).

FEATURES AND BENEFITS

- Easy to gun out and tool
- Outstanding UV Stability
- Non sagging properties
- Highly elastic
- Sea water and hydrolysis resistant
- Excellent adhesion to nonferrous metals

TECHNICAL PROPERTIES

Chemical base	1-component polyurethane
Color (CQP001-1)	Black, white
Cure mechanism	Moisture-curing
Density (uncured)	1.3 kg/l
Non-sag properties	Good
Application temperature	10 – 35 °C
Skin time (CQP019-1)	60 minutes ^A
Open time (CQP526-1)	45 minutes ^A
Shrinkage (CQP014-1)	1 %
Shore A hardness (CQP023-1 / ISO 7619-1)	35
Tensile strength (CQP036-1 / ISO 527)	2 MPa
Elongation at break (CQP036-1 / ISO 527)	500 %
Tear propagation resistance (CQP045-1 / ISO 34)	5 N/mm
Service temperature (CQP509-1 / CQP513-1)	-50 – 90 °C
Shelf life (CQP016-1)	12 months ^B



CQP = Corporate Quality Procedure

^{A)} 23 °C / 50 % r. h.

^{B)} storage below 25 °C



SIKA SERVICES AG
Tueffenwies 16
8048 Zurich
Switzerland

Contact:
Phone: +41 58 436 40 40
Fax: +41 58 436 55 30
www.sika.com/marine

BUILDING TRUST

