

PRODUCT DATA SHEET

SikaWrap®-430 G

Woven unidirectional glass fibre fabric, designed for structural strengthening applications as part of the Sika strengthening system.

DESCRIPTION

SikaWrap®-430 G is a unidirectional woven glass fibre fabric designed for installation using the dry or wet application process.

USES

SikaWrap®-430 G may only be used by experienced professionals.

Structural strengthening of reinforced concrete, masonry, brickwork and timber elements or structures, to increase flexural and shear loading capacity for:

- Improved seismic performance of masonry walls
- Increasing the strength and ductility of columns
- Enabling changes in use / alterations and refurbishment
- Correcting structural design and / or construction defects
- Increasing resistance to seismic movement
- Improving service life and durability
- Structural upgrading to comply with current standards
- Blast mitigation (accidents or terrorism)
- Electrical environments that ask for non-conductive material

CHARACTERISTICS / ADVANTAGES

- Manufactured with heat-set weft fibres to keep the fabric stable
- Multifunctional fabric for use in many different strengthening applications
- Flexible and accommodating to different surface planes and geometry (beams, columns, chimneys, piles, walls, soffits, silos etc.)
- Low density for minimal additional weight
- Cost effective in comparison to traditional strengthening techniques
- Very low electrical conductivity

PRODUCT INFORMATION

| Fibre orientation | 0° (unidirectional) | | |
|-------------------------|--------------------------------|---|--|
| Warp | White glas | White glass fibres 98 % | |
| Weft | White the | White thermoplastic heat-set fibres | |
| | 2 % | | |
| E-glass fibres | | | |
| | Fabric length per roll | Fabric width | |
| 1 roll in cardboard box | ≥ 50 m | 600 mm | |
| | Warp Weft E-glass fibres | Warp Weft White glas White glas White the 2 % E-glass fibres Fabric length per roll | |

Product Data Sheet SikaWrap®-430 G

August 2020, Version 02.01 020206020020000001

| Shelf life | 24 months from date of production | | | | |
|--|--|---------------------------------|-----------------------|---|--|
| Storage conditions | Store in undamaged, original sealed packaging, in dry conditions at temperatures between +5 °C and +35 °C. Protect from direct sunlight. | | | | |
| Dry fibre density | 2.56 g/cm ³ | | | | |
| Dry fibre thickness | 0.168 mm (based on total glass content) | | | | |
| Area density | 430 g/m² + 10 g/m² (glass fibres only) | | | | |
| Dry fibre tensile strength | 2 500 N/mm ² (measuerd on roving) | | | (EN 2561) | |
| Dry fibre modulus of elasticity in tension | 72 000 N/mm² | | | (EN 2561) | |
| Dry fibre elongation at break | 2.7 % (measured on roving | 2.7 % (measured on roving) | | | |
| TECHNICAL INFORMATION | | | | | |
| Laminate nominal thickness | 0.168 mm | 0.168 mm | | | |
| Laminate nominal cross section | 168 mm² per m width | | | | |
| Laminate tensile strength | Average 1 500 N/mm² | Characteristic 1 200 N/mm² | | (EN 2561*) (ASTM 3039*) | |
| Laminate modulus of elasticity in tension | Average 70 kN/mm² | Characteristic 68 k/Nmm² | | (EN 2561*) (ASTM 3039*) | |
| | * modification: sample with 50 mm Values in the longitudinal direction of the fibres Single layer, minimum 27 samples per test series | | | | |
| Laminate elongation at break in tension | 2.14 % | | (Ł | (based on EN 2561) pased on ASTM 3039) | |
| Tensile resistance | Average 252 kN/m | Characteristic 202 kN/m | | (based on EN 2561) (based on ASTM 3039) | |
| Tensile stiffness | Average 11.8 MN/m | Characteristic 11.4 MN/m | | (based on EN 2661) (based on ASTM 3039) | |
| | 11.8 kN/m per ‰ elonga- tion | 11.4 kN/m per ‰ elonga- tion | | - | |
| SYSTEMS | | | | | |
| System structure | The system build-up and configuration as described must be fully complied with and may not be changed. Concrete substrate adhesive primer Sikadur®-330 Impregnating / laminating resin Sikadur®-330 or Sikadur®-300 Structural strengthening fabric SikaWrap®-430 G | | | | |
| | For detailed information on Sikadur®-330 or Sikadur®-300, together with the resin and fabric application details, please refer to the Sikadur®-330 Sikadur®-300 Product Data Sheet and the relevant Method Statement. | | | ne Sikadur®-330 or | |
| APPLICATION INFORMATION | N | | | | |
| Consumption | Dry application with Sikadu First layer including primer | | 1.2–1.6 kg/m² | | |
| | Following layers | | 1.0 kg/m ² | | |





Wet application with Sikadur®-300, primer Sikadur®-330

| Primer layer | 0.5–0.7 kg/m ² | | |
|---------------|---------------------------|--|--|
| Fabric layers | 0.7 kg/m ² | | |
| Di | | | |

Please also refer to the relevant Method Statement for further information.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Minimum substrate tensile strength: 1.0 N/mm² or as specified in the strengthening design.

Please also refer to the relevant Method Statement for further information.

SUBSTRATE PREPARATION

Concrete must be cleaned and prepared to achieve a laitance and contaminant free, open textured surface. Please also refer to the relevant Method Statement for further information.

APPLICATION METHOD / TOOLS

The fabric can be cut with special scissors or a Stanley knife (razor knife / box-cutter knife). Never fold the fabric.

SikaWrap®-430 G is applied using the dry or wet application process.

Please refer to the relevant Method Statement for details on the impregnating / laminating procedure.

FURTHER INFORMATION

Method Statements

Ref. 850 41 02: SikaWrap® manual dry application Ref. 850 41 03: SikaWrap® manual wet application Ref. 850 41 04: SikaWrap® machine wet application

IMPORTANT CONSIDERATIONS

- SikaWrap®-430 G shall only be applied by trained and experienced professionals.
- A specialist structural engineer must be consulted for any structural strengthening design calculation.
- SikaWrap®-430 G fabric is coated to ensure maximum bond and durability with the Sikadur® adhesives / impregnating / laminating resins. To maintain and ensure full system compatibility, do not interchange different system components.
- SikaWrap®-430 G can be over coated with a cementitious overlay or other coatings for aesthetic and / or protective purposes. The over coating system selection is dependent on the exposure and the project specific requirements. For additional UV light protection in exposed areas use Sikagard®-550 W Elastic, SikaColor®-670 W or Sikagard®-680 S.

 Please refer to the Method Statement of SikaWrap® manual wet application (Ref. 850 41 03) or SikaWrap® machine wet application (Ref. 850 41 04) for further information, guidelines and limitations.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must



be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Hellas ABEE

15 Protomagias Str. 14568 Kryoneri Attica-Greece Tel.: +30 210 8160 600 Fax: +30 210 8160 606 www.sika.gr | sika@gr.sika.com





Product Data Sheet SikaWrap®-430 GAugust 2020, Version 02.01
020206020020000001

SikaWrap-430G-en-GR-(08-2020)-2-1.pdf

